## **PCT**

# WORLD INTELLECTUAL PROPERTY ORGANIZATION International Bureau



## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification <sup>5</sup>:

E04D 5/02

(11) International Publication Number: WO 91/00945

(43) International Publication Date: 24 January 1991 (24.01.91)

(21) International Application Number: PCT/DK90/00179

(22) International Filing Date: 10 July 1990 (10.07.90)

(30) Priority data: 3401/89 10 July 1989 (10.07.89) DK

(71) Applicant (for all designated States except US): A/S JENS VILLADSENS FABRIKER [DK/DK]; Mileparken 38, DK-2730 Herlev (DK).

(72) Inventors; and
(75) Inventors/Applicants (for US only): HOLBEK, John [DK/DK]; Nymøllevej 29, DK-2800 Lyngby (DK). WORRE, Kim [DK/DK]; Wilkensvej 7, DK-2000 Frederiksberg (DK). BECK, Bjarne, Kufall [DK/DK]; Selma Lagerløfs Allé 42, DK-2860 Søborg (DK).


(74) Agent: LEHMANN & REE; Frederiksberg Allé 26, DK-1820 Frederiksberg C (DK).

(81) Designated States: AT (European patent), BE (European patent), CA, CH (European patent), DE (European patent)\*, DK (European patent), ES (European patent), FI, FR (European patent), GB (European patent), IT (European patent), JP, LU (European patent), NL (European patent), NO, SE (European patent), US.

#### **Published**

With international search report. In English translation (filed in Danish).

(54) Title: A BITUMINOUS COATING MATERIAL AND A PROCESS FOR PRODUCING A BITUMINOUS COATING ON A SUPPORT



#### (57) Abstract

A bituminous sheet or web coating material (1) is on the one side provided with a heat activatable adhesive layer (3) optionally covered by a plastic film (5), wherein the adhesive layer is provided with a pattern of close grooves (4) with intermediate unbroken ridges, and a process for forming a coating on a support is performed by heating such coating material (1) to decomposition of said plastic film (5) and activation of the adhesive layer (3), the activated adhesive layer (3) being pressed against the support, e.g. a roof.

#### **DESIGNATIONS OF "DE"**

Until further notice, any designation of "DE" in any international application whose international filing date is prior to October 3, 1990, shall have effect in the territory of the Federal Republic of Germany with the exception of the territory of the former German Democratic Republic.

### FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

	•			•		
AT	Austria		ES	Spain -	мс	Monaco
AU	Australia		FI	Finland	MG	Madagascar
BB	Barbados		FR	Franco	ML	Mali
BE	Belgium		GA	Gabon	MR	Mauritania
BF	Burkina Fasso		GB	United Kingdom	MW	Malawi .
BG	Bulgaria		GR	Greece	NL	Netherlands
BJ	Benin		HU	Hungary	NO	Norway
BR	Brazil		ľТ	Italy	PL	Poland
CA	Canada		JР	Japan	RO	Romania
CF	Central African Republic	-	KP	Democratic People's Republic	SD	Sudan
ČG	Congo			of Korea	SE	Sweden
CH	Switzerland		KR	Republic of Korea	SN	Senegal
CM	Cameroon	•	LI	Liechtenstein	SU	Soviet Union
DB	Germany	-	LK	Sri Lanka	TD	Chad
DK	Denmark		LU	Luxembourg -	TG	Togo
	_ <del></del>				US	United States of America
	•					

A bituminous coating material and a process for producing a bituminous coating on a support

The present invention relates to a bituminous coating sheet or web material provided on the one side with a heat activatable adhesive layer which is optionally coated with a plastic film.

In particular, the invention relates to a bituminous web-formed coating material for the formation of a roof covering.

10

25

30

5

It is known to produce roofings by using roofing felt webs, i.e. bituminous felt lengths, coated with a plastic film of e.g. polyethylene or polypropylene and having a thickness of about 10  $\mu$ m,

It is the main function of the plastic film to prevent adjacent parts of the roofing felt webs from sticking to each other when said webs are stored and transported in rolls.

The heating of the roofing felt webs is typically carried out by use of propane gas burners.

When the flame, which has a typical temperature of 1000-1300°C, is directed towards the plastic film coated adhesive layer, the plastic film decomposes and burns away and the adhesive layer is activated. The use of such gas burners is associated with a certain fire hazard as sometimes the support or other parts of the roof construction catch fire.

The said flame heating is further associated with the drawback that the decomposition of the plastic film is often incomplete and therefore areas remain where the adhesive layer is covered with film residues and, as a consequence, the desired adhesion is not obtained.

DK patent publication No. 150 586 B discloses a process for producing a bituminous coating on a support, provided with pressure equalization zones. In this known process a bituminous web material which, on the adhesive side being provided with rows of projections of an adhesive consisting of a mixture of bitumen and a

thermoplastic elastomer, is adhered to the support. Said rows are typically spaced apart about 30 mm and the projections have a maximum length of 50 mm, a typical width of 15 mm and a height of 1-3 mm.

5

The formation of said projections on the bituminous sheet material is effected by producing initially a sand-strewn bituminous web material and then rolling thereon the adhesive in its melted state using a pattern embossing roll.

10

15

30

35

The known material is appropriate for the formation of a coating with pressure equalization zones, but it is unsuitable for the formation of a fully adhered coating as, although the adhesive is heated enough for the projections to spread, it is not possible to obtain a uniform adhesive layer. Moreover, the known material is associated with the drawback that it is difficult to obtain complete removal of the film described above, as a part of said film remains on top of the said projections.

- The coating material according to the invention is characterized in that a pattern of parallel grooves and intermediate unbroken ridges is provided in the adhesive layer, the distance between adjacent grooves not exceeding 10 mm.
- The coating material according to the invention is surprisingly found to present a variety of technical advantages.

Firstly, such a material may be used not only for forming a fully adhered coating on a support, viz. by heating all parts of the groove-patterned adhesive layer, but also for forming a coating which prevents humidity and/or air under pressure in entrapped zones from accumulating during the coating process. The latter is obtained by heating the adhesive layer in such a manner that it is adhered to the support in separate zones, the grooves of the non-adhered zones serving as pressure equalization channels.

As compared to the coating material disclosed in DK patent publication No. 150 586, the material according to the invention is moreover simpler and thus less expensive to produce, the production

5

10

20

25

30

35

thereof not requiring the application of an additional adhesive layer of a particular composition.

Furthermore, said groove pattern in the adhesive layer permits a vastly enhanced heat exchange between the hot gas stream on the one side and the plastic film and the adhesive layer on the other side when the removal of a plastic film fixed to the adhesive layer is to be carried out prior to adhering the material to a support. The improved heat exchange causes the removal of the plastic film to be substantially faster and more efficient and the adhesive layer to be more efficient activated than when the known coating material disclosed above is used.

The practical consequence is that when using a propane gas flame for heating the energy requirement is reduced.

In practice the reduced energy requirement means that it is possible to increase the laying out rate of roofing felt having an adhesive layer, which consists primarily of bitumen, from about 1.0 m/min to about 1.4 m/min which means that the energy consumption per m is reduced from about 61 g gas/m to about 45 g gas/m.

When laying out roofing felt with a 15 cm overlap, experiments in practice have proved it possible to increase the rate from 0.8 m/min to about 1.5 m/min, which means that the energy consumption is reduced from 63 W/m to 33 W/m.

The surprisingly improved heat exchange is also expressed by the fact that, when carrying out the process according to the invention, flameless heating of the plastic film and the adhesive layer may be carried out, said flameless heating, which may e.g. be carried out with an air stream having a temperature of from 200 to 800°C, having surprisingly proved to effect the complete removal of the plastic film and the activation of an adhesive layer of bitumen.

The use of such a flameless gas stream of a relatively low temperature eliminates substantially fire hazards.

The distance between the grooves in the adhesive layer is, as stated

5

10

15

20

25

30

35

above, no more than 10 mm and according to a preferred embodiment the distance is between 1 and 5 mm which means that the grooves are situated relatively closely to each other. The height of the projections as measured from the bottom of the grooves is preferably comprised within the range of from 0.5 to 6 mm and particularly preferred within a range of from 1 to 3 mm.

Preferably the grooves in the adhesive layer extend in the longitudinal direction of the web material and thus, they can be produced by combing of the adhesive layer in connection with the production of the sheet material when the adhesive layer is still hot and viscous.

However, said grooves may also extend perpendicularly to said direction or at any other angle relative to the longitudinal direction.

The adhesive layer may consist of usual adhesive asphalt (bitumen), but it may also contain a self-adhesive polymer or resin.

The plastic film may e.g. have a thickness of from about 10  $\mu$ m, but in practice films with thicknesses of from 3 to 30  $\mu$ m can be used.

The invention further relates to a process for producing a water-proof, bituminous coating on a support and in particular a roof covering, wherein a sheet or web coating material, which, on the one side being provided with a heat activatable adhesive layer covered by a plastic film, is heated to decompose said plastic film and to activate the adhesive layer and the activated adhesive layer is pressed against the support, said process being characterized in that the material according to the invention described above is used as the coating material.

A particularly preferred embodiment of the process according to the invention is characterized in that the heating is carried out with a flameless hot air stream.

Such air stream may e.g. be produced by electrically heating a stream of atmospheric air.

The heating may also be carried out by heat radiation, e.g. by use of internally heated heating means or by IR heat radiation.

The invention will be further described in greater detail with reference to the accompanying drawing which represents a schematical perspective view of a preferred embodiment for a roofing web according to the invention.

In the drawing 1 denotes a roofing web comprising a felt layer 2 and an adhesive layer 3. The adhesive layer 3 is on the inside of the web 1 provided with grooves 4 which extend in the longitudinal direction of the web material 1. The grooved adhesive layer 3 is coated with a plastic film 5 which abuts substantially only the tops of the ridges between the grooves 4.

5

30

35

#### Claims .


- 1. A bituminous sheet or web coating material provided on the one side with a heat activatable adhesive layer optionally covered by a plastic film, c h a r a c t e r i z e d in that the adhesive layer is provided with a pattern of parallell grooves and intermediate unbroken ridges, the distance between adjacent grooves not exceeding 10 mm.
- 10 2. A coating material according to claim 1, c h a r a c t e r i z e d in that the distance between adjacent grooves is between 1 and 5 mm.
- 3. A coating material according to claims 1 or 2, c h a r a c t e r i z e d in that the height of the ridges as measured from the bottom of the grooves is from 0.5 to 6 mm and preferably from 1 to 3 mm.
- A coating material according to any one of claims 1, 2 or 3,
   c h a r a c t e r i z e d in that the grooves extend in the longitudinal direction of the sheet material.
- 5. A coating material according to any one of the preceding claims, c h a r a c t e r i z e d in that the plastic film is of a thickness of from 3 to 30  $\mu$ m.
  - 6. A process for the production of a bituminous coating on a support, wherein a sheet or web coating material provided with a heat activatable adhesive layer covered by a plastic film is heated to decompose the plastic film and to activate the adhesive layer, and the activated adhesive layer is pressed against the support, c h a r a c t e r i z e d in using a coating sheet material in which the adhesive layer is provided with a pattern of parallel grooves and intermediate unbroken ridges, the distance between adjacent grooves not exceeding 10 mm.
    - 7. A process according to claim 6, characterized in in that the distance between adjacent grooves is from 1 to 5 mm.

8. A process according to claims 6 or 7, c h a r a c t e r i z e d in using a flameless hot air stream for heating the plastic film and the adhesive layer.

. 5

PCT/DK90/00179

1/1



## INTERNATIONAL SEARCH REPORT

International Application No. PCT/DK 90/00179

		N OF SUBJECT MATTER (If several classifi		BK 307 00173		
According IPC5: E	to Interna 04 D	tional Patent Classification (IPC) or to both Na 5/02	itional Classification and IPC			
II. FIELD	S SEARCH	IED				
		Minimum Documen	tation Searched <sup>7</sup>			
Classificati	Classification System Classification Symbols					
IPC5		E 04 D		,		
		Documentation Searched other to the Extent that such Documents				
05 514 5						
SE,UK,	-1,NO c	classes as above				
		ONSIDERED TO BE RELEVANT <sup>9</sup>				
Category *		ion of Document, <sup>11</sup> with indication, where app	<del> </del>	Relevant to Claim No. <sup>13</sup>		
<b>Y</b> 	F/	, 150586 (AKTIESELSKABET JE ABRIKER) 1 December 1986, se page 5 - page 6 kample 1	NS VILLADSENS	1-8		
Y	U) 19	3, 2544361 (DE. KOHL GMBH & ND BAUTENSCHUTZMITTEL-FABR) October 1984, ee details 3 and 4	Z CIE DACHBELAG- (K)	1-8		
Υ	17	, 2146270 (TAJIMA ROOFING (7 April 1985, see figure 2 etails 26 and 27	CO. LTD.)	1-8		
			<b></b>			
* Specia "A" doc con	the international filing date lict with the application but le or theory underlying the					
"E" earlier document but published on or after the international filing date "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another						
"O" dod	ce, the claimed invention a an inventive step when the e or more other such docu- pobvious to a person skilled					
other means  "P" document published prior to the international filing date but later than the priority date claimed  "&" document member of the same patent family						
IV. CERT	FICATION					
۱	ctober	mpletion of the International Search	Date of Mailing of this International S	search Report		
Internation	al Searchi	ng Authority	Signature of Authorized Officer			
SWEDISH PATENT OFFICE Vilho Juyonen						

# ANNEX TO THE INTERNATIONAL SEARCH REPORT ON INTERNATIONAL PATENT APPLICATION NO.PCT/DK 90/00179

This annex lists the patent family members relating to the patent documents cited in the above-mentioned international search report. The members are as contained in the Swedish Patent Office EDP file on 90-08-28The Swedish Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

	Patent document ted in search report	Publication date	Patent family member(s)		Publication date
DK-B-	150586	86-12-01	NONE		
FR-A3-	2544361	84-10-19	BE-A- LU-A- NL-A-	899326 85277 8401052	84-07-31 84-10-24 84-11-01
GB-A-	2146270	85-04-17	AT-B- BE-A- CA-A- CH-A-B- DE-A- FR-A- JP-A- NL-A- SE-B- SE-A- US-A-	389137 900565 1230723 666224 3432813 2551790 60059184 8402757 462221 8404346 4636414	89-10-25 85-01-02 87-12-29 88-07-15 85-03-15 85-04-05 85-04-01 90-05-21 85-03-13 87-01-13